

# Purolite® C100EFM

Polystyrenic Gel Strong Acid Cation  
Resin Sodium form, Fine Mesh  
Grade, Potable Water Grade

## PRINCIPAL APPLICATIONS

- Softening - Potable Water
- Food and beverage processing
- Softening - Industrial

## ADVANTAGES

- High operating capacity
- Superior regeneration
- Lower rinse volumes
- Superior kinetic performance
- Low extractables

## SYSTEMS

- Coflow regenerated systems

## REGULATORY APPROVALS

- Certified by the WQA to NSF/ANSI-61 Standard

## TYPICAL PACKAGING

- 1 ft<sup>3</sup> Sack
- 25 L Sack
- 5 ft<sup>3</sup> Drum (Fiber)
- 1 m<sup>3</sup> Supersack
- 42 ft<sup>3</sup> Supersack

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Sulfonic Acid
Ionic Form	Na <sup>+</sup> form
Total Capacity	1.9 eq/L (41.5 Kgr/ft <sup>3</sup> ) (Na <sup>+</sup> form)
Moisture Retention	45 - 50 % (Na <sup>+</sup> form)
Particle Size Range	210 - 600 µm
< 210 µm (max.)	1 %
Uniformity Coefficient (max.)	1.6
Reversible Swelling, Na <sup>+</sup> → H <sup>+</sup> (max.)	10 %
Reversible Swelling, Ca <sup>2+</sup> → Na <sup>+</sup> (max.)	8 %
Specific Gravity	1.27
Shipping Weight (approx.)	790 - 825 g/L (49.4 - 51.6 lb/ft <sup>3</sup> )
Temperature Limit	120 °C (248.0 °F)



**Americas**  
T +1 610 668 9090  
F +1 610 668 8139  
americas@purolite.com

**Europe**  
T +44 1443 229334  
F +44 1443 227073  
europe@purolite.com

**Asia Pacific**  
T +86 571 876 31382  
F +86 571 876 31385  
asiapacific@purolite.com